

Electrical resistance spot brazing of two different alloys

V. Lazić, D. Arsić & M. Djordjević

Faculty of Engineering, University of Kragujevac, Kragujevac, Serbia

R.R. Nikolić & B. Hadzima

Research Center, University of Žilina, Žilina, Slovakia

ABSTRACT: The general problems related to electrical resistance brazing of various metals were considered in this paper. In brazing different electrodes and technological parameters are used. For experimental purposes, electrodes were made of highly alloyed tungsten steel and of copper with graphite and tungsten inserts, so the symmetrical temperature field was obtained. Success of brazing was determined by testing the mechanical properties, micro hardness and microstructure of the brazed joint. Hardness measurement results suggested the strain hardening of the steel thin sheets, what imposed necessity of recrystallization annealing. It was necessary to apply both the flux and the silver solder for joining, since copper and iron are poorly mutually soluble. When the metallurgy problems were solved and the optimal brazing parameters selected, the optimal mechanical properties were achieved, which were experimentally confirmed.

1 INTRODUCTION

Due to low solubility of copper-based alloys' and steel's basic components, i.e., copper and iron, brass and steel are difficult to join by the welding procedures. This problem can be solved by inserting the inter-layer made of the third metal, which is soluble both in copper and in iron. In this case, that is the silver solder in the form of a foil with addition of the flux in the form of the thin coating. To enable successful joining of those alloys it was necessary to perform numerous tests, which made possible selection of the soldering parameters, which gave the needed mechanical properties of the brazing joint. Besides that, it was also necessary to check the micro hardness and microstructure of the joint. Hardness measurements results shown hardening of the steel thin sheet, due to action of the compressive force during the brazing, what imposed the necessity for recrystallization annealing of the joint for improving the structure, namely the mechanical properties and the corrosion resistance.

Electric resistance brazing is the process of joining metals where the Joule's effect – RI^2 is used as the heat source. There are three methods of electrical resistance brazing: *spot wise*, used for joining steel and brass thin sheets, for joining parts in electronics, etc.; *seam wise*, used for making the box-like parts where the hermetic joints are required and *butt brazing*, used for brazing the sintered cutting platelets onto the steel holder of the cutting tools, Radomski and Ciszewski (1985), AMS-Metals Handbook (1979), JMM Brazing materials and applications (1967).

Heat amount (Q), released within the closed power circuit of the total electric resistance (R), through which flows the electric current (I), during the time (t), amounts to $Q = RI^2t$. The released heat amount is not the same in all the parts of the circuit, but it is proportional to the electric resistance within particular part. This is why one can obtain, by construction measures and selection of the electrode material, the highest resistance at the thin sheets overlap. Since it is not possible to prevent completely the heating of the rest of the circuit, it has to be reduced by water-cooling of the electrodes. Electrodes material's characteristics are given in [Table 1](#).

